

FRV1106

Description

FRV1106 is a one-component, ready-to-use fluorosilicone adhesive sealant that cures to a tough resilient silicone rubber on exposure to atmospheric moisture at room temperature. FRV1106 adhesive sealant is a paste consistency, fluid resistant product designed for use in fuel, solvent and chemical environments.

Key Features and Typical Benefits

- Resist swelling by hydrocarbon solvents, dimethyl silicone fluids and fuels
- One component product
- Primerless adhesion to many substrates
- Room temperature cure
- Non-sag paste consistency
- Retain elastomeric properties at temperatures of -60 °C to 204 °C for long periods and to 260 °C for short periods.
- Ozone resistant, high quality weatherability
- Excellent electrical insulation properties

Typical Physical Properties

Uncured Properties:	FRV1106
Color	Red
Consistency	Paste
Specific Gravity	1.45
Application Rate, gm/min.	88
Tack Free Time, minutes	20
Cure Through Time, hours	24

Cured Properties ^(A)	
Mechanical:	
Hardness, Shore A	39
Tensile Strength, (psi) MPa	(485) 3.33
Elongation, %	200
Tear Strength, (psi) MPa	(61) 0.42
Peel Strength, (lbs/in) kg/mm	(26) 0.46

Typical property data values should not be used as or to develop product specification.

^(A)Cure time 7 days at 25 °C (77 °F), 50 % relative humidity.

Typical Fluid Immersion Properties ^(A)

	Volume Swell %	Shore A Hardness pts change	Tensile Strength % change	Elongation % change
FRV1106				
Toluene	16.6	-4	-30	-8
Mineral Spirits	2.2	-4	-27	-4
Methylene Chloride	61.0	-8	-29	12
JP-4	5.4	-2	-28	23
Fuel B	17.9	-2	-30	-32

Typical property data values should not be used as or to develop product specifications.

^(A)Cured 7 days before immersion. Properties obtained after 7 days immersion at room temperature.

Information is provided for customer convenience. These properties are not tested on a routine basis.

Note: These sealants are not for use in delicate electrical and electronic applications in which corrosion of copper, brass and other sensitive metals is undesirable.

Physical Properties

In addition to the effects of temperature and relative humidity, development of maximum bond strength will depend on joint configuration, degree of confinement, sealant thickness and substrate porosity. Normally, sufficient bond strength for the FRV1106 will develop in 18-24 hours to permit handling of parts. Stress should not be applied to the bonded joint until full adhesive strength has developed. Eventually the adhesive strength of the bond will exceed the cohesive strength of the silicone adhesive sealant itself. Always allow maximum cure time available for best results.C

Potential Applications

FRV1106 adhesive sealant is ideally suited for use in applications where resistance to the swelling effects of fuels, oils, solvents and chemicals is needed. Providing a formed-in-place gasket for pipe junctions in chemical plants, sealing seams on liquid holding tanks and bonding sensing devices in a gas tank are typical applications. The paste consistency of these sealants allows them to be applied even on vertical and overhead surfaces in thickness up to 6 mm (1/4 in.).

Instructions for Use

Surface Preparation

FRV1106 adhesive sealant will bond to many surfaces without the aid of a primer. Surfaces should be thoroughly cleaned with a suitable solvent to remove dirt, oil, grease and other contaminants. If scale or corrosion is present, the surface should be cleaned with an abrasive wheel or sandpaper followed by a solvent cleaning.

Application and Cure Time Cycle

FRV1106 adhesive sealant may be applied directly to clean or primed substrates. The cure process begins with the formation of a skin on the exposed surface of the sealant and progresses inward through the material. At 25 °C (77 °F) and 50 % relative humidity, these sealants will form a surface skin that is tack-free to the touch in 20-25 minutes. Once this tack-free skin begins to form, further tooling of the sealant is not recommended.

As the adhesive sealant cures, acetic acid vapours are released. As the curing reaches completion, the noticeable acetic odour will diminish.

Because these adhesive sealants cure by reacting with atmospheric moisture higher temperature and humidity will accelerate the cure process while lower temperature and humidity will retard the process.

Exact cure time will depend on temperature, humidity, sample thickness and sealant configuration.

Packaging and Dispensing

FRV1106 adhesive sealant is supplied ready to use in 5.4 fl. oz. SEMCO⁽¹⁾ cartridges.

⁽¹⁾The SEMCO cartridge is designed for use with a hand or air operated sealant gun manufactured by the Semco Company.

Clean Up and Removal

Before curing, solvent systems such as methyl ethyl ketone (MEK) and acetone are most effective. After cure, selected chemical strippers which will remove the silicone rubber are available from other manufacturers. Specific product information may be obtained on request.

These products are manufactured and marketed for Industrial use only. Safety Data Sheets are available upon request from Momentive Performance Materials. Similar information for solvents and other chemicals used with Momentive products should be obtained from your suppliers. When solvents are used, proper safety precautions must be observed.

Patent Status

本書のいかなる内容も、関連特許が存在しないことを暗示したものではありません。またいかなる特許についても、その権利者による許可なしに、その特許が対象とする発明を実施するための許可、誘因または推奨を構成することはできません。

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

お問合せ窓口

製品の価格、取り扱い状況およびご注文については、[Momentive.com/Contact us/ CustomerService/](https://www.momentive.com/Contact-us/CustomerService/)からカスタマーサービスへご連絡ください。

パンフレットおよび技術情報については、弊社ウェブサイトwww.momentive.comをご覧ください。

免責条項:

モメンティブ・パフォーマンス・マテリアルズならびにその子会社および関係会社(以下、総称して「サプライヤー」といいます)の素材、製品およびサービスは、サプライヤーの標準販売条件に基づき販売されています。この標準販売条件は、該当する販売代理店契約または販売契約に含まれており、注文確認書や請求書の裏面に印刷され、また要求に応じて提供可能です。本書に記載の情報、推奨、または提言は、誠意をもって提供されていますが、サプライヤーは明示的にも黙示的にも、(i)本書に記載の結果が最終使用条件下でも得られること、および(ii)製品、素材、サービス、推奨または提言に取り入れられている設計の有効性もしくは安全性について、いかなる保証もいたしません。サプライヤーの標準販売条件に定めのあるものを除き、サプライヤーおよびその代理人は、本書に記載の素材、製品またはサービスの使用によって生じたいかなる損害に対しても責任を負わないものとします。サプライヤーの素材、サービス、推奨、または提言が、ユーザー自身の特定の使用目的に適しているか否かの判断については、各ユーザー自身が全面的に責任を負います。各ユーザーは、すべてのテストや分析を特定および実施して、サプライヤーの製品、素材、またはサービスが組み込まれている最終製品が安全であり、最終使用条件における使用に適していることを確認する必要があります。サプライヤーの署名入りの書面による合意がない限り、本書もしくはその他の文書または口頭による推奨または提言は、サプライヤーの標準販売条件の規定または本免責条項の変更、修正、優先、または権利放棄とはみなされないものとします。本書に含まれる素材、製品、サービスまたは設計の使用可能性または使用提案に関するいかなる記載も、当該使用または設計を対象とするサプライヤーの特許その他の知的財産権に基づくライセンスを付与することを意図してはならず、あるいはライセンスの付与と解釈してはならず、また、何らかの特許その他の知的財産権を侵害する素材、製品、サービスまたは設計の使用の提案を意図してはならず、また使用提案として解釈してはなりません。

Momentive および Momentiveのロゴは、Momentive Performance Materials Inc.の商標で

す。