

## Silopren\* LSR2610

### Silopren\* LSR2610

#### Description

**Silopren LSR 2610** is a two-component liquid silicone rubber for injection moulding processes. **Silopren LSR 2610** shows in comparison to **Silopren LSR 2010** a lower viscosity, improved tear resistance and a higher reactivity. Therefore, it is also possible to reduce the vulcanisation temperature while maintaining a standard crosslinking rate. The increased reactivity does not affect the properties of the vulcanisate.

#### Key Features and Benefits

Vulcanisates consisting of **Silopren LSR 2610** are distinguished by the following properties:

- high reactivity, lower viscosity, shorter cycle time
- excellent thermal stability
- high stability and flexibility at low temperatures
- good rubber-like properties, high tear resistance
- high stability to ozone and ultraviolet light
- outstanding resistance to ageing,
- excellent dielectric behaviour over a wide range of temperatures,
- not readily combustible, does not melt or drip
- easy pigmentable with the LSR Colour Pastes

#### Typical Physical Properties

Typical Properties of the Rubber:			
		A-part	B-part
Appearance		translucent	translucent

Viscosity in Pa•s $\gamma = 10 \text{ s}^{-1}$ at 20°C	DIN 53018	90	67
--	-----------	----	----

The pot-life of the mixture of the two components (closed vessel) at 20°C is usually three days. Increased temperatures reduce the pot-life.

Typical Properties of the Vulcanizate:

Mixing ratio of components A : B = 1 : 1.

Vulcanization: 10 min. 175°C + 4 hrs 200°C post-cure

Density	DIN 53 479 A	g/cm <sup>3</sup>	1.04
Shore A hardness	DIN 53 505		16
Tensile Strength	DIN 53 504 S2	N/mm <sup>2</sup>	2.9
Elongation at Break	DIN 53 504 S2	%	560
Tear Strength	ASTM D 624 die B	N/mm	9
Compression Set	DIN 53 517 (22 h at 175 ° C)	%	12

**Potential Applications**

Because of the outstanding properties **Silopren LSR 2610** is particularly suitable for the following elastomeric articles: stoppers, vibration dampers, shoe inserts s.o.

**Processing Recommendations**

Ready-to-use mixtures (of the components A and B) are fed directly to the injection moulding machine from the original containers by means of a metering and mixing unit. The mixture, consisting of the two components in the ratio 1:1, is injected into the heated mould. At mould temperatures of 140 - 200 ° C, the addition-crosslinking silicone rubber vulcanises free of dissociation products within a few seconds. High curing speed and ease of demoulding permit fully automated production of large numbers of articles in short cycle times.

With **Silopren LSR 2610** it is possible to produce combined elements with a wide range of thermoplastic materials.

**Containers**

**Silopren LSR 2610** is available in 20 kg pails and 200 kg drums.

**Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

**Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### **Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### **Contact Information**

For product prices, availability, or order placement, contact our customer service at [Momentive.com/CustomerService/](http://Momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### **DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED**

**HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Silopren is a trademark of Momentive Performance Materials Inc.

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**