

Niax* Catalyst C-31

Urethane Additevs - Rigid Foam

Description

Niax Catalyst C-31 is a delayed action catalyst for the manufacture of rigid polyurethane and polyisocyanurate foams produced by continuous lamination or mould injection processes. This catalyst can facilitate accelerated foam hardening and improved green strength and foam adhesion properties and is an excellent candidate for the production of PUR or PIR foam high thickness panels.

Key Features and Typical Benefits

- High selectivity toward PIR reactions, to boost the formation of a fully cross-linked polymer network after gelation occurs
- Improved surface cure, stiffness and reduced swelling of PIR insulation boards and metal faced panels.
- Improved cure of PUR foam where slow reactivity or low mould temperature tends to affect the polymer cure.

Typical Physical Properties

Appearance	Clear, pale yellow liquid
Viscosity at 25 °C, cSt	60
Water Content %	2
Specific Gravity at 25 °C	1.18
OH value mg KOH/g	620 (745 including water)

Typical physical properties are average data and should not be used as or to develop product specifications.

General Considerations For Use

Typical product usage level is between 1 and 5 parts per one hundred parts polyol.

Niax Catalyst C-31 can be used in addition to an existing catalyst package while maintaining the required reaction profile.

If used in combination with a blowing catalyst, it can enable improved flow without affecting cure time.

Use of Niax Catalyst C-31 in combination with Niax Catalyst C-5 and Niax Catalyst Potassium Octoate LV and a suitable Niax Silicone is recommended.

Detailed guidelines on application and usage of Niax Catalyst C-31 can be obtained by contacting the nearest Momentive Customer Service Center or your local Momentive contact.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services

will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Niax is a trademark of Momentive Performance Materials Inc.1033

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.