

## SNAPSIL™ TSE322S SILICONE ADHESIVE SEALANT

### Description

TSE322S is a one-component, heat curable silicone adhesive sealant paste, which bonds to many substrates without a primer.

### Key Features and Typical Benefits

- One component product - no mixing required
- Primerless adhesion to many types of substrates
- No cure by-products, low linear shrinkage
- Non-corrosive to metals and sensitive substrates
- Excellent dielectric properties
- Outstanding performance over a wide temperature range

### Typical Physical Properties (JIS K 6249)

<u>Property</u>	<u>Unit</u>	<u>Value</u>
<b>Uncured Properties</b>		
Colour		Light Blue
Appearance		Semi-flowable
Viscosity (23 °C)	Pa·s	70
Density (23 °C)	g/cm <sup>3</sup>	1.26
<b>Cured Properties (cured 1 hour at 150 °C)</b>		
Hardness (Type A)		37
Elongation	%	230
Tensile Strength	MPa	3.6
Adhesive Strength <sup>(1)</sup>	MPa	2.5

Dielectric Strength	kV/mm	25
Dielectric Constant (60Hz)		3.1
Dissipation Factor (60Hz)		0.006
Volume Resistivity	$\Omega \cdot \text{cm}$	$1.0 \times 10^{15}$
Thermal Coefficient of Expansion	1/K	$2.1 \times 10^{-4}$
Thermal Conductivity	W/m.K	0.29

Typical physical properties are average data and should not be used as or to develop product specifications.

<sup>(1)</sup>Aluminum lap shear

## CAUTION

SNAPSIL TSE322S silicone adhesive can generate flammable hydrogen gas upon contact with acidic, basic, or oxidizing materials. Such contact should be avoided.

## Processing Recommendations

### Compatibility

SNAPSIL TSE322S silicone adhesive will cure in contact with most clean, dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfur-containing materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a gummy appearance of the SNAPSIL TSE322S silicone adhesive at the interface between the adhesive and the substrate to be bonded. It is recommended that a sample patch test be performed with the SNAPSIL TSE322S silicone adhesives to determine substrate compatibility.

### Surface Preparation

The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of SNAPSIL TSE322S silicone adhesive and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the adhesive.

### Bonding

SNAPSIL TSE322S silicone adhesive offers outstanding adhesion characteristics to a wide variety of different substrates without the need of a primer.

**Suitable substrates**

Metals : aluminum, copper, Ni plate, stainless steel

Plastics : PPS, PBT, Epoxy resin, Polyester, Phenolic resin

Inorganics : Glass, Ceramics

Rubbers : Silicone HCR

**Not Suitable substrates**

Plastics : PP, PE, Fluorocarbon resin

Rubbers : Silicone RTV, Sulfur vulcanized rubbers, Fluorocarbon rubber

For difficult-to-bond-to substrates, or where more aggressive chemical adhesion is desired, the adhesion may be enhanced by using Momentive's SS4155 silicone primer. To apply the primer, first thoroughly clean the surface and let dry. Then apply a uniform film (0.01 mm - 0.02 mm) of SS4155 silicone primer and allow the primer to air-dry for one hour or more.

**Curing**

SNAPSIL TSE322S silicone adhesive requires elevated temperatures in order to achieve full cure. Typical cure times and temperatures are as follows:

<b>Temperature</b>	<b>TSE322S Silicone Adhesive</b>
100 °C	3 hours
120 °C	90 minutes
150 °C	60 minutes

Note: Test data. Actual results may vary.

The actual cure time is affected by such things as cross-sectional thickness of the TSE322S silicone adhesive, heat capacity of the overall assembly and efficiency and type of oven used (i.e. convection, infrared)

**Specifications**

Typical physical properties are average data and should not be used as or to develop product specifications. Assistance and specifications are available by contacting Momentive Performance Materials Technical Service RTV1 and RTV2.

**Availability**

SNAPSIL TSE322S is available in tubes, 333 ml cartridges, 1kg cans and 20 kg pails.

**Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

**Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

**Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

**Contact Information**

For product prices, availability, or order placement, contact our customer service at [Momentive.com/CustomerService/](http://Momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

**Momentive and the Momentive logo are trademarks of Momentive Performance**

**Materials Inc.**