

SILQUEST* Y-15744 silane

SILANES - ADHESIVES & SEALANTS ADDITIVES



Silquest Y-15744 silane is an amino functional silane oligomer that is an excellent candidate to consider for use in a broad range of applications to promote adhesion between organic / inorganic substrates and organic polymers including, but not limited to, in moisture curing formulations such as hybrid or silicone-based sealants, adhesives and coatings.

Its proprietary structure can help confer good wetting properties to the adhesive or sealant formulation in which it is incorporated.

This typically results in:

- adhesion on concrete and difficult, low polarity substrates
- moderate hydrophobicity with little impact on the formulation curing rate
- improved adhesion in wet environments

The typical mechanical properties of this adhesion promoter are similar to, or only slightly softer than, those achieved when Silquest A-1110 aminopropyltrimethoxysilane is at the same addition level. However, adhesion to low polarity plastics typically is significantly better.

In some filled formulations, it has been observed that Silquest Y-15744 silane can help improve the compatibility between the resin and the fillers. This can result in an increased transfer of mechanical strength from the mineral to the formulation. In those cases, a better tear resistance and higher toughness have been observed in the cured product.

Key Features and Typical Benefits

The chemical properties of Silquest Y-15744 silane typically offer improved performance as an adhesion promoter on both porous and difficult organic substrates.

- primary Amino Groups – Co-catalytic effect for curing of the coating, adhesive or sealant formulation
- methoxy Silane Ester – Rapid attainment of bond strength

- ability to improve wetting properties, even on substrates with low surface tension.
- improved adhesion on damp masonry and concrete
- strong, weather resistant bonds

Typical Physical Properties

Physical Form	Light yellow liquid
Percent Active Material	100
Specific Gravity, 25/25°C	1.01
Flash Point, Pensky-Martens Closed Cup, ⁽¹⁾ °C (°F)	80 (176)
Boiling Point at 4.0 mm Hg, °C (°F)	>210 (>392)

(1) ASTM Method D93

Typical physical property values should not be used as specifications.

SILQUEST* Y-15744 silane

Potential Applications

For adhesives, sealants and coatings, Silquest Y-15744 silane may be considered for achieving weather- and moisture-resistant bonds to substrates such as glass, metal, but also on more difficult surfaces like concrete and plastics. Durable water-resistant bonds are generally achieved when the silyl portion of this aminosilane is condensed with an inorganic surface and is covalently bonded with the resin matrix of the coating, sealant or adhesive. The typical addition level of this product lies between 0.5 and 1.0%, based on the total formulation.

Example Sealant Formulation

The following sealant formulation was used to evaluate the performance of Silquest Y-15744 silane.

Table 1: Sealant Formulation

	Percentage
SPUR+ 1015 LM prepolymer	23.14%
Plasticizer	18.51%
UV Stabilizer	0.46%
Thixotropic Agent	0.23%
Titanium Dioxide	1.16%
Calcium Carbonate	55.05%
Moisture Scavenger (Silquest A-171* silane)	0.35%
Adhesion Promoter	0.58%
Catalyst	0.05%

SPUR+ 1015 LM prepolymer and Silquest A-171 silane are available from Momentive Performance Materials.

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

The physical properties of one-part SPUR+ prepolymer-based sealant incorporating Silquest Y-15744 silane were evaluated using European test methods ISO 37, 868.

Silquest Y-15744 silane was compared with Silquest A-1110 silane (aminopropyltrimethoxysilane), the most commonly used amino silane adhesion promoter in hybrid sealants.

Table 1: Impact of Silquest Y-15744 silane on Sealant Mechanical Properties⁽¹⁾ Compared to Silquest A-1110 silane:

Adhesion Promoter	Unit	Silquest A-1110 silane	Silquest Y-15744 silane
F max	N/mm ²	2.18	1.92
F at rupture	N/mm ²	2.15	1.84
Elongation	%	378	384
Mod 100	N/mm ²	1.02	0.9
Shore A	-	35.5	34.3
TFT (Skin formation time)	Min	55-60	55-60
Aspect		Good	Good

(1) The numbers reported in this table represent average values measured on the cured formulation described in Table 1.

Note: Test data. Actual results may vary.

Table 3: Adhesion Properties on Dry Substrates (ISO 8510-2)⁽²⁾

Adhesion Promoter	Silquest A-1110 silane		Silquest Y-15744 silane	
	N/mm	% of cohesive failure	N/mm	% or cohesive failure
Concrete ISO 13640 type 1	1.85	80	1.93	95
Concrete ISO 13640 type 2	2.13	80	2.04	90
Glass	1.61	100	1.60	100
Aluminum	1.65	100	1.89	100
AlMg1 (alloy 5005 A - windows grade)	2.42	100	2.17	100
Galvanized Steel	1.93	100	1.95	100
Stainless Steel	1.77	100	1.93	100
ABS	0.12	0	1.70	100
PS	1.05	0	2.01	100
PA6	1.89	100	2.06	100
PC	2.04	100	1.79	100
POM (polyoxymethylene)	0.80	0	1.55	50
PMMA	0.64	0	2.16	100
PVC Rigid (CAW Simona)	2.72	100	1.98	100
PVC Soft	1.15	50	1.48	100

(2) The numbers reported in this table represent average values measured on the cured formulation described in Table 1.

Note: Test data. Actual results may vary.

SILQUEST* Y-15744 silane

Potential Applications (continued)

Table 4: Adhesion Properties on Wet Substrates (ISO 10591)⁽²⁾

Adhesion Promoter	Silquest A-1110 silane		Silquest Y-15744 silane	
	N/mm	% of cohesive failure	N/mm	% or cohesive failure
Concrete ISO 13640 type 1	0.72	10	1.23	20
Concrete ISO 13640 type 2	0.49	0	1.11	5
Glass	1.80	100	2.35	100
Aluminum	1.48	100	2.08	100
AlMg1 (alloy 5005 A – windows grade)	1.86	100	1.86	100
Galvanized Steel	1.81	100	1.83	100
Stainless Steel	1.72	100	1.92	100
ABS	0.18	0	1.37	75
PS	0.12	0	1.17	50
PA6	1.68	100	2.06	100
PC	1.60	100	1.98	100
POM (polyoxymethylene)	0.73	0	1.13	40
PMMA	0.72	0	1.85	100
PVC Rigid (CAW Simona)	2.21	100	1.75	100
PVC Soft	1.32	50	1.47	100

⁽²⁾ The numbers reported in this table represent average values measured on the cured formulation described in Table 1.

Note: Test data. Actual results may vary.

Emergency Service

Momentive Performance Materials maintains an around-the-clock emergency service for its products.

Location	Emergency Service Provider	Emergency Contact Number
Mainland U.S., Puerto Rico	CHEMTREC	1-800-424-9300
Alaska, Hawaii	CHEMTREC	1-800-424-9300
Canada	CHEMTREC	1-800-424-9300
Europe, Israel	NCEC	+44 (0) 1235239670
Middle East	NCEC	+44 (0) 1235239671
Asia Pacific (except China)	NCEC	+44 (0) 1235239670
China	NCEC	+86-10-5100-3039
Latin America (except Brazil)	NCEC	+44 (0) 1235239670
Brazil	SOS Cotec	08000111767 or 08007071767
All other locations world wide	NCEC	+44 (0) 1235239670
At sea	Radio U.S. Coast Guard in U.S. waters NCEC in International waters	+44 (0) 1235239670

For Health related calls, contact Momentive Performance Materials at +1-518-233-2500 (English only).

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

Patent Status

Technical subject matter in this publication is described and protected by one or more pending US patent applications and foreign counterparts.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.momentive.com or, upon request, from any Momentive Performance Materials representative. Use of other materials in conjunction with Momentive Performance Materials products may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Customer Service Centers

Worldwide Hotline

T +1 800 295 2392 / +1 607 786 8131
F +1 607 786 8309

North America

cs-na.silicones@momentive.com

Silicones – Fluids, Urethane Additives, Silanes, Specialty Coatings, RTVs and Elastomers

T +1 800 523 5862 / +1 800 334 4674
F +1 304 746 1654 / +1 304 746 1623

Consumer Sealants/ Construction Sealants and Adhesives

T +1 877 943 7325
F +1 304 746 1654

Latin America

cs-la.silicones@momentive.com

South America

T +55 11 4534 9650
F +55 11 4534 9660

Mexico and Central America

T +52 55 2169 7670
F +52 55 2169 7699

Europe, Middle East, Africa and India

cs-eur.silicones@momentive.com

T +00 800 4321 1000 / +40 21 3111848

Pacific

cs-ap.silicones@momentive.com

China

T +800 820 0202 / +86 21 3860 4892

Japan

T +0120 975 400 / +81 276 20 6182
F +81 276 31 6259

Korea

T +82 2 6201 4600
F +82 2 6201 4601

Malaysia

T +60 3 9206 1555
F +60 3 9206 1533

Thailand

T +66 2207 3456
F +66 2207 3488

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silquest. Silquest A-171 and SPUR+ are trademarks of Momentive Performance Materials Inc.

The Momentive logo is a trademark of Momentive Performance Materials Holdings LLC.



22 Corporate Woods Boulevard
Albany, NY 12211 USA

+1 800 295 2392
+1 607 786 8131
momentive.com