

SilFORT™ UVHC5000 Clear Coat

Product Description

SilFORT UVHC5000 clear coat is a clear, solvent-based, UV-curing coating used on polycarbonate parts to help protect against abrasion, chemical damage and degradation caused by ultraviolet radiation and weathering. It is an excellent candidate to consider for use on headlamp lenses for forward lighting, exterior/interior trim and exterior/interior polycarbonate sheets. It complies with the ECE automotive forward lighting regulations^① and is AMECA listed for five years exposure in Florida and Arizona.

Key Features and Typical Benefits

- 5-year weatherability listing
- Enhanced resistance to microcracking
- Transparency
- Excellent adhesion to various plastics
- Easy-to-clean properties
- High chemical resistance
- ECE compliant and AMECA listed
- Recoverability and re-use of overspray
- Application by spray, flow, dip, roller and ink jetting

Potential Applications

- Automotive forward headlight lenses
- High performance sheets and films

Typical Physical Properties

Property	Unit	Typical Value
Physical form	-	Liquid
Appearance	-	Yellow
Solids content	% by weight	approx. 45
Kinematic viscosity (@ 25°C)	cSt	approx. 10
Density (@ 25°C)	g/cm ³	approx. 1.01
Shelf life ^②	Months	15

Typical properties are average data and are not to be used as or to develop specifications.

^①Based on the requirements as of April 2022

^②From date of manufacture, in original unopened container

General Considerations for Use

Application method	Spray, flow, dip, roller coating & ink jetting
Reducing solvents	1-Methoxy-2-propanol (CAS#107-98-2) 2-Butanol (CAS#78-92-2) 2-Propanol (CAS#67-63-0) ^③
Relative humidity (application and ambient flash off)	Max. 65%
Room temperature flash off	20 – 30°C for 1 – 3 minutes
Pre-heating	1.5 to 6 minutes to reach 65 – 95°C part surface Temperature ^{④ ⑤}
Intermediate cool down	Optional
Typical UV-cure	3 – 12 J/cm ² UV-A (EIT Inc. Power Puck II Device) ^{⑥ ⑦}
Recommended hardcoat thickness ^⑧	8 – 16 µm ^⑨
Recommended thickness of interpenetrating layer	> 1 µm ^⑩

For best results in applying clear coat, filter the coating solution by combining a 5 µm pre-filter, followed by a 1 µm absolute gel-filter.

To help ensure adequate UV-cure, work with the UV-lamp supplier to select UV-reflectors that are appropriate for the parts to be treated. Do not expose product to any source of visible white light prior to UV-cure. To avoid exposure when white light is present, do not use semi-transparent pipework.

Packaging

Currently available in:

25 kg pail

180 kg drum

5G-pail (18.16 kg)

55G-drum (181.6 kg)

^③ Other compatible solvents may be considered

^④ Longer pre-heating times may be required when using convection heating instead of IR-heating

^⑤ Modified, high heat resistant PC grades may require higher pre-heat temperatures

^⑥ For applications that mainly require chemical resistance against solvents such as ketones, the product may be cured at a lower UV-dosage (1.5 J/cm²)

^⑦ Use of un-doped, medium pressure mercury arc lamps or microwave powered Hg lamps with > 80 W/cm power is recommended. Typical UV-irradiance is 0.2 to 0.6 W/cm²

^⑧ Refractive Index n = 1.5

^⑨ In areas protected from sunlight, layers of > 3 µm may achieve required abrasion & chemical resistance, as well as basic weathering protection. In cases, higher film thickness (up to 20 µm) was applied, typically no detrimental effects on coating performance of headlamp lenses were reported

^⑩ Higher thickness of 2 µm up to 6 µm may further improve adhesion after harsh humidity cycles

Contact Information

For product prices, availability or order placement, contact customer service at Momentive.com/contact/customer-service

For literature and technical assistance, visit our website at: www.momentive.com

Telephone

Americas	EMEA	China	Japan	South Korea	South East Asia, Australia & New Zealand
+1 800 295 2392	+40 213 044229	800 820 0202	0120 975 400	+82 2 6201 4600	
+1 704 805 6946		+86 21 3860 4892	+81 27620 6182		+60 3 9206 1543

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.



Hudson River Road Waterford, NY
12188 USA www.momentive.com

Copyright 2020 Momentive Performance Materials Inc. All rights reserved.